

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Claims 1 - 14. (Cancelled).

15. (Previously Presented) Partly hydrophobic silica particles, said partly hydrophobic silica particles having a contact angle θ in air for water of less than 180° , a degree of coverage τ of the surface of the silica with silylating agent residues, based on the total silica particle surface area, of $1\% < \tau < 50\%$, a density of surface silanol groups SiOH ranging between a minimum of 0.9 and a maximum of 1.7 SiOH/nm² particle surface area, and having a carbon content of more than 0% and up to 2.0% by weight, and a methanol number of less than 30, said partly hydrophobic silica prepared by a process comprising silylating silica particles prepared under anhydrous conditions, with

I) an organosilane of the formula



where n is 1, 2 or 3

or mixtures of these organosilanes,

R^1 being a monovalent, optionally halogenated hydrocarbon radical having 1 to 24 carbon atoms, being identical or different at each occurrence, and being saturated, aromatic, monounsaturated, or polyunsaturated,



X each independently being halogen, a nitrogen radical, OR^2 , $OCOR^2$, or $O(CH_2)_xOR^2$,

R^2 being hydrogen or a monovalent hydrocarbon radical having 1 to 12 carbon atoms, and

x being 1, 2 or 3;



or

II) an organosiloxane composed of units of the formula



where R^1 is as defined above, or mixtures thereof,
the number of these units in one organosiloxane being at least 2; and I and II being used alone or in any desired mixtures in a total amount of from 0.015 mmol/g to 0.15 mmol/g per 100 m²/g of silica BET surface area measured by the BET method in accordance with DIN 66131 and 66132.

16. (Previously Presented) The particles of claim 15, wherein said silylating is performed with an organosiloxane composed of units of the formula (II)



where R^1 is as defined above, or mixtures thereof,
the number of these units in one organosiloxane being at least 2; II being used in a total amount of from 0.015 mmol/g to 0.15 mmol/g per 100 m²/g of silica BET surface area measured by the BET method in accordance with DIN 66131 and 66132.

17. (Previously Presented) The particles of claim 15, wherein said silylating is performed with an organosilane of the formula



where n is 1, 2, or 3, or a mixture of these organosilanes, where R^1 is a C₁₋₂₄ hydrocarbon radical selected from the group consisting of alkyl radicals, alkenyl radicals, aryl radicals, and alkylaryl radicals, each R^1 being the same or different,

X each independently being halogen, a nitrogen radical, OR², OCOR², or
O(CH₂)_xOR²,

R^2 being hydrogen or a monovalent hydrocarbon radical having 1 to 12 carbon atoms, and
x being 1, 2 or 3.

18. (Previously Presented) The particles of claim 17, wherein said step of silylating is performed with a mixture of at least one organosilane of the formula $R_n^3SiX_{4-n}$ with an organosiloxane of the formula (II).

19. (Currently Amended) The particles of claim 17, wherein each $[[R^3]] R^1$ individually is selected from the group consisting of methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, decyl, dodecyl, hexadecyl, octadecyl, phenyl, biphenyl, naphthyl, benzyl, ethylphenyl, tolyl, and xylyl radicals.

20. - 29. (Cancelled).

30. (Previously Presented) The particles of claim 15, wherein said partly hydrophobic silica has a methanol number less than 20.

31. (Previously Presented) The particles of claim 15, wherein said partly hydrophobic silica has a carbon content of 0.1 to 0.5 weight percent per each 100 m²/g of surface area.

32. (Currently Amended) The composition of claim 17, wherein $[[R^7]] R^1$ is independently selected from the group consisting of methyl, octyl, and vinyl.

33. (Currently Amended) ~~The composition~~ partly hydrophobic silica particles of claim 17, wherein at least one organosilane is selected from the group consisting of methyltrichlorosilane, dimethyldichlorosilane, trimethylchlorosilane, and hexamethyldisilazane.

34. (Currently Amended) ~~The composition~~ partly hydrophobic silica particles of claim 15, wherein the contact angle θ is between 100° and 0°.

35. (Currently Amended) The ~~composition~~ partly hydrophobic silica particles of claim 15, wherein the contact angle θ is between 90° and 0° .

36. (Currently Amended) The ~~composition~~ partly hydrophobic silica particles of claim 15, wherein the density of surface silanol groups is between 1.2 and 1.7 SiOH per nm^2 of particle surface.